

KingGrout[®] PG200

High strength low exothermic pourable epoxy resin grout.

DESCRIPTION

KingGrout PG200 is a three component, high strength, low exothermic and free flowing epoxy resin grout. KingGrout PG200 is suitable for grouting large gaps from 10 to 400 mm at high ambient temperatures of up to 55°C.

APPLICATIONS

KingGrout PG200 is ideally designed for use in the following applications:

- ☐ Machine base plates.
- ☐ Heavy crane rails.
- ☐ Bearing plinths.
- ☐ Anchoring of steel fixings.
- ☐ High speed turbines.
- ☐ Grouting areas where occasional chemical spillage may occur.

ADVANTAGES

- ☐ Low heat generating grout for large gaps and high ambient temperatures.
- ☐ Resistant to dynamic loading.
- ☐ Non-shrink and low creep characteristics under continuous loading.
- ☐ Exceptional high compressive, flexural and tensile strengths.
- ☐ Extremely dense.
- ☐ Exceptional bond to concrete and steel surfaces.
- ☐ Good chemical resistance.
- ☐ High ultimate and early strengths.

METHOD OF USE

Substrate Preparation

- ☐ The Substrate should be sound, clean and free from contamination. Surface laitance should be removed by scabbling or grit blasting.
- ☐ Steel surfaces should be grit blasted to remove all rust and scale.
- ☐ Concrete surfaces should be dry.
- ☐ Holes drilled for anchor bolts should be thoroughly cleaned from dust and loose debris using suitable brush or compressed air.

MIXING

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

TECHNICAL PROPERTIES @ 35°C:

| | |
|--|--|
| Compressive strength: BS6319, Part 2 : 1983 | ≥ 50 MPa @ 3 days ≥ 80 MPa @ 7 days |
| Flexural strength: BS6319, Part 3 : 1990 | ≥ 27 MPa @ 7 days |
| Tensile strength: BS6319, Part 7 : 1985 | ≥ 12 MPa @ 7 days |
| Recommended working ambient temperature: | 15 - 55°C |
| Crack formation tem- perature @ 400 mm: | No cracks or bleeding |
| Peak exothermic tem- perature @ 55°C: ASTM D2471 | 62°C |
| Peak exothermic time @ 55°C: ASTM D2471 | 45 min |
| Gel time @ 55°C: ASTM D2471 | 150 - 180 min |
| Water absorption: ASTM C413 | < 0.15% |
| Mixed density: | 1.95 ± 0.05 g/cm ³ |
| Working life: | 3 - 6 hrs @ 25° C 2 - 4 hrs @ 35° C |
| VOC: ASTM D2369 | < 10 g/ltr (complies with LEED) |

The entire content of the Hardener pack should be added to the Base pack. Care should be taken to ensure that the bottom and the product sides are thoroughly scraped and used. Mix the two components for 2 minutes. The filler should be gradually added while mixing. Mixing should continue for 3 minutes or until a uniform consistency obtained.

THICKNESSES AND SIZE LIMITATIONS

KingGrout PG200 is suitable for grouting large gaps from 10 to 400 mm. For greater thicknesses, multiple layers can be applied after initial curing of the previous layer.

KingGrout® PG200

PLACING AND FINISHING

Under Base plate:

Enough material should be available to achieve a continuous fill and to complete the work. Pouring of the mixed grout should be started from one side only to avoid air entrapment. To obtain maximum flow distance, a side shutter feed with 100 mm side height should be erected and used to build the required head. At 100 mm of head, a flow distance of 2100 mm can be achieved at gap thicknesses of 40 mm @ 25°C ambient temperatures.

Formwork:

As the mixed grout possesses high fluid characteristics, all formwork and shutters should be water tight. This can be achieved by sealing underneath the formwork and at the joints by using an appropriate mastic.

Notes:

If temperatures are less than 20°C, the cure rate will be slow, but eventually will go to completion if the temperatures remain above 10°C.

CLEANING

All tools should be cleaned immediately after finishing using a suitable epoxy thinner. Hardened materials should be cleaned mechanically.

PACKAGING

KingGrout PG200 is available in 15 kg packs (7.5 litre).

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative.

KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's Qatar facility are manufactured under a management system independently certified to conform to the requirements of the quality standard ISO 9001.

* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.

KingKrete-Qatar/KingGrout_PG200_02/v2/07_18

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.